

Technical Data Sheet **HyGlaze™ Bund Coat**

HyGlaze™ Bund Coat

Highly chemical resistant bund coating

Product Description

HyGlaze Bund Coat is an aliphatic solvent-based UV stable polyurethane coating with excellent abrasion and chemical resistance and has good weathering properties. It is available with a matt finish as standard (coloured options) & gloss finish for clear. Satin and gloss (coloured) finishes including water-based options are available on request

As from 24th August 2023, adequate training is required before industrial or professional use of this product

Typical Uses

Designed for areas of harsh or extended chemical attack, $HyGlaze^{TM}$ Bund Coat is suitable for chemical bunds as well as general floor areas. It is ideal for industrial and commercial floors and chemical process industries.

Suitable substrates: Following application of the appropriate primer, $HyGlaze^{TM}$ Bund Coat

may be applied to concrete, render, brick, aluminium and steel.

Colour HyGlaze™ Bund Coat is available in a selection of 12 stock colours, or

in a large range of BS4800 and RAL specifications (subject to minimum quantity). We can make it to your specification on any order over 30 units.

Packaging: HyGlaze™ Bund Coat is supplied in pre-measured quantities as a two

part 5.0kg unit, comprising an epoxy resin blend Part 'A' and hardener

Part 'B'

Direction For Use

Surface Preparation

THOROUGH SUBSTRATE PREPARATION IS ESSENTIAL.

Prior to application of *Hy-Glaze™ Bund Coat*, the surface should be primed with *Polycote EP Primer* or *WD Primer*, depending on the type of substrate. Please contact Polycote Technical Helpline and prepare the surface in accordance with the appropriate primer Data Sheet. Should the time lapse between priming and top coat exceed 48 hours, abrade the primer to ensure intercoat adhesion

Mixing

Prior to mixing, both components should be kept at a temperature between 15°C and 20°C. Having fully prepared the substrate, stir the individual components before mixing together. As pigment may 'sink', ensure that the mixing is very thorough and from the bottom of the container. Add the hardener to the coloured resin and thoroughly mix for at least 5 minutes. For best results use a heavy duty slow speed drill with a mixing paddle.

Application

Apply by brush, roller or squeegee, making sure that the surface is completely covered. Always ensure a constant wet edge and work within the pot life of the material.

Make sure the coating is not overlapped in any area and apply in one direction only. Two coats are recommended in areas of high chemical aggression. The ambient temperature of the areas should not fall below 10°C throughout the application and curing period.

Application Temperature

Normal application temperature range is between +15°C and +20°C. The maximum substrate and atmospheric relative humidity should be 75%.

Pot Life & Curing Time

At 20°C the pot life once mixed is 30 minutes. Recoat time (min.) is 16 hours and (max.) 48 hours. *HyGlaze Bund Coat* can take light pedestrian traffic after 12 hours, light wheeled traffic after 24 hours and heavy duty traffic after 48 hours. Full strength is achieved after 7 days. Please note at lower temperatures, the above cure times will be extended.

Technical Data After 28 Days at 20°C Compressive Strength: N/A

Tensile Strength: N/A
Bond Strength: > 1.5 N/mm²

Abrasion Resistance: N/A
Slip Resistance Dry > 50

Pendulum Test to BS7976-2: Wet and Anti Slip finish. VOC: < 490g/l - Clear

< 386g/l - Coloured Based on a fully mixed unit

Chemical Resistance Excellent general chemical resistance.

Polycote UK LLP

01234 846400 | uksales@polycote.com | www.polycote.com

Coverage

Cleaning

Shelf Life & Storage

Health & Safety

Any Questions

Approximately 4m²/kg per coat, up to 20m² per 5kg unit, will depend on the surface porosity and its texture.

Tools and equipment should be cleaned whilst resin is still wet with Solvent Cleaner. Hands and skin should be cleaned immediately with Organic Hand Cleaner.

Shelf life in unopened containers is approximately 12 months subject to conditions of storage. Store in a cool, dry, at temperatures between 10°C to 25°C, frost-free environment away from sources of ignition.

Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.

Please do not hesitate to contact us for advice regarding the use of this product or its suitability for your particular application.

Our aim is to provide all the technical help you need to make an informed choice and achieve total success.

Polycote Technical Helpline: 01234 846400

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.