Rooflex™Sealant

High performance polymeric roofing and joint sealant



"maintenance made easy"



PRODUCT DESCRIPTION

Rooflex™Sealant is a gun-applied moisture curing modified polymer compound with outstanding resistance to weathering and joint movement, coupled with excellent adhesive properties.

TYPICAL USES

Rooflex™ Sealant is ideal for repairing joints, gaps, cracks and holes in all types of roof area prior to application of waterproof coatings. It is recommended for use with most Polycote roof waterproofing systems. If in doubt, please contact Polycote technical helpline.

SUITABLE SUBSTRATES

Rooflex™ Sealant may be applied to asphalt, bitumen, felt, asbestos, concrete, roofing tiles, slate, brick, stone, cast iron, galvanised steel, aluminium, lead, zinc, glass and timber.

COLOUR

Rooflex[™] Sealant is grey in colour.

PACKAGING

Rooflex[™] Sealant is supplied in 380ml cartridges, complete with polyethylene nozzles.



PHYSICAL PROPERTIES

Typical Shore A Hardness 55		
Chemical Resistance Resists most dilute acids & alkalis		
UV Resistance	Very Good	
Movement Accommodation Butt Joints (Tension and Compression) 35%		
Lap Joints (Shear)	70%	
Modulus @ 100% Extension	1.12N/mm ²	
Maximum Extension	220%	
Tensile Strength at Break	1.85N/mm ²	
Service Temperature -40°C to +120°C		

DIRECTIONS FOR USE

SURFACE PREPARATION

THOROUGH JOINT PREPARATION IS ESSENTIAL.

For optimum joint movement accommodation, the joint must be **NOT LESS THAN** 6mm wide.

Narrower joints and cracks subject to movement must therefore be raked out and opened out to this minimum size. The prepared surface should be dry, clean, sound and free of flaking or loose material, moss or fungal growth. Any previous joint sealant material should be removed.

Porous surfaces should be sealed with SP Primer before applying Rooflex Sealant.

PRIMING

A single coat of *SP Primer* should be applied if appropriate using a clean dry brush and allowed to dry for 60 minutes. *Rooflex Sealant* should then be applied as soon as possible and in any case within 8 hours.

APPLICATION

Apply using a caulking gun. Cut the nozzle at an angle to facilitate the placing of the sealant.

CURING TIME

At 20°C/65% relative humidity, *Rooflex Sealant* will form a tack-free skin after 20 minutes and cure at a rate of 2mm per 24 hours.

APPLICATION TEMPERATURE

Rooflex Sealant should be applied at a temperature between +5°C and +35°C.

COVERAGE

Nominal	Linear Metres
Joint Size	per 380ml Unit
6mm x 6mm	10.55m
9mm x 6mm	7m
12mm x 9mm	3.52m
18mm x 10mm	2.11m
25mm x 10mm	1.52m

CLEANING

Tools and equipment should be cleaned whilst material is still wet using Solvent Cleaner. Hands and skin should be cleaned immediately with organic hand cleaner.

SHELF LIFE & STORAGE

Shelf life in unopened containers is 12 months, subject to conditions of storage.

Store in a cool, dry frost-free environment away from sources of ignition.

$C \in$

Polycote UK, Centre Point, Wolseley Road, Woburn Road Industrial Estate, Kempston, Beds MK42 7FF

14

EN15651 -1: F – EXT-INT ROOFLEX SEALANT

1 Part Sealant for Facade Elements for exterior and interior application.

HEALTH & SAFETY

Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.

ANY QUESTIONS?

Please do not hesitate to contact us for advice regarding the use of this product or its suitability for your particular application. Our aim is to provide all the technical help you need to make an informed choice and achieve total success.

Polycote Technical Helpline

01234 846400

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure for himself that the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.

REV: 06/17

Polycote UK
Centre Point • Wolseley Road • Woburn Road Industrial Estate
Kempston • Beds • MK42 7EF
Technical Helpline: 01234 846400

